

Curing Room						Natural Curing						
	Total Thickness	Adhesion to Steel	Roll Ball Tack	Weight	Temp.	Total Thickness	Adhesion to Steel	Roll Ball Tack	Weight	Temp.		
Day 1	59-60	920 g	1.5-2 cm	73.15 kg	Passes Cold & Heat Test	59-60	909 g	1.5-2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes.		
Day 2	59-61	896 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	881 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
Day 3	58-59	881 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	848 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
Day 4	58-59	869 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-59	859 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
Day 5	58-59	874 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	900 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
Day 6	59-60	881 g	2 cm	73.15 kg	Passes Cold & Heat Test	59-61	875 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
Day 7	59-61	835 g	2 cm	73.15 kg	Passes Cold & Heat Test	57-59	823 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 8	60-61	840 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	829 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 9	58-59	815 g	2 cm	73.15 kg	Passes Cold & Heat Test	59-61	860 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 10	59-61	877 g	2 cm	73.15 kg	Passes Cold & Heat Test	59-61	848 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 11	59-60	821 g	2 cm	73.15 kg	Passes Cold & Heat Test	59-61	856 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 12	58-60	837 g	2 cm	73.15 kg	Passes Cold & Heat Test	59-62	839 g	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 13	60-61	874 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	801 g (air pockets)	2 cm	58.35 kg	Pass In Cold Test. Heat Test 180° angle fails but 90° angle passes		
DAY 14	58-60	854 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	862 g	2 cm	58.35 kg	Passes Cold & Heat Test		
Day 15	58-60	837 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	868 g	2 cm	58.35 kg	Passes Cold & Heat Test		
Day 20	58-59	835 g	2 cm	73.15 kg	Passes Cold & Heat Test	58-60	890 g	2 cm	58.35 kg	Passes Cold & Heat Test		